




TEST REPORT


No.202011200871-1

Client	(No.8 Chuangye Road, Fenghuang Town, Zhangjiagang City, Jiangsu Province, China)			
Sample Name	(CPE apron)	Trademark	—	
	Style No.	—	Specification	—
	Color	Blue	Sample Grade	—
	Sample Quantity	2Pcs	Safety Level	—
	Manufacturer	(Zhangjiagang Wenhao Industrial Co., Ltd.) (No.8 Chuangye Road, Fenghuang Town, Zhangjiagang City, Jiangsu Province, China)		
Test Type	Commission Test			
Sample Receiving Date	2020/04/21			
Testing Period	2020/04/21~2020/04/23			
Test Standard(s)	GB/T 4744-2013 Textiles—Testing and evaluation for water resistance—Hydrostatic pressure method》 GB/T 4745-2012 Textiles - Testing and evaluation for water resistance - Spray test method》 QB/T 4999-2016 Daily rainproof—Poncho and raincoat》			
Test Conclusion	For details, please read the summary table of testing results.			
Remark	—			



Approve 

Check 

workout 

202011200871-1

No.	Test Items		Unit	Technical Requirement	Test Results	Individual Judge
1	(Hydrostatic pressure)		kPa	≥ 1.67 Client Requirement)	3.0	Pass
2	(Spray rating)		(Grade)	≥ 4 Client Requirement)	4-5	Pass
3	Appearance quality)		—	(Products shall be clean, free from stain, broken or crack phenomena)	(Qualified)	Pass
4	(Colour fastness) (Plastic materials)	(Change)	—	Shall not lose colors)	fading)	Pass